

Příloha P II Naměřená data bukových vzorků

	Obsah vody v dřevině [%]		
Č.m.	Doma	Venku	Voda
1.	7,5	8,7	17,7
2.	6	9,3	16
3.	6,6	9,1	15,2
4.	5,8	9,5	16,3
5.	5,6	9,3	16,4
Průměr	6,3	9,2	16,3
Smdch	0,77	0,30	0,90

Výška dřevěného bukového hranolu plochým hrotem

	BUK-DOMA [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	21,060	21,012	20,930	20,864	20,830
2.	21,049	21,047	20,924	20,863	20,760
3.	21,056	21,038	20,918	20,854	20,804
4.	21,061	20,987	20,917	20,835	20,882
5.	21,066	20,999	20,903	20,849	20,881
Průměr	21,058	21,017	20,918	20,853	20,831
Smdch	0,0063	0,0254	0,0101	0,0119	0,0521
Median	21,060	21,012	20,918	20,854	20,830

	Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]	
0,174	0,215	0,314	0,379	0,401	

Výška dřevěného bukového hranolu špičatým hrotem

	BUK-DOMA [mm]				
Č.M.	30/100	Zobrazovaná oblast	0 [W]	60/100 [W]	70/100 [W]
1.	20,725		20,725	20,646	20,567
2.	20,959	20,790	20,696	20,635	20,599
3.	20,937	20,881	20,712	20,639	20,550
4.	20,970	20,850	20,745	20,629	20,587
5.	20,972	20,785	20,701	20,616	20,533
6.	20,965	20,802	20,696	20,621	20,468
7.	20,948	20,848	20,675	20,622	20,465
8.	20,963	20,846	20,698	20,616	20,519
9.	20,976	20,855	20,665	20,676	20,587
10.	20,908	20,868	20,793	20,629	20,542
Průměr	20,956	20,832	20,711	20,633	20,542
Smdch	0,0203	0,0358	0,0368	0,0181	0,0471
Median	20,961	20,847	20,700	20,629	20,546

Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
0,152	0,276	0,397	0,474	0,566

	BUK-VENKU [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	21,062	20,972	20,898	20,834	20,795
2.	21,031	20,963	20,917	20,842	20,765
3.	21,031	20,967	20,913	20,863	20,791
4.	21,037	20,976	20,909	20,839	20,784
5.	21,057	20,974	20,916	20,833	20,793
Průměr	21,044	20,970	20,911	20,842	20,786
Smdch	0,0148	0,0053	0,0077	0,0122	0,0122
Median	21,037	20,972	20,913	20,839	20,791

	Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]	
0,110	0,184	0,243	0,312	0,368	

	BUK-VENKU [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	20,969	20,815	20,748	20,674	20,592
2.	20,449	20,778	20,750	20,684	20,602
3.	20,932	20,869	20,717	20,677	20,632
4.	20,902	20,863	20,766	20,605	20,530
5.	20,915	20,821	20,703	20,610	20,504
6.	20,918	20,794	20,739	20,629	20,482
7.	20,906	20,803	20,782	20,662	20,542
8.	20,882	20,811	20,671	20,661	20,578
9.	20,926	20,821	20,753	20,625	20,603
10.	20,924	20,822	20,767	20,649	20,618
Průměr	20,872	20,820	20,740	20,648	20,568
Smdch	0,1504	0,0281	0,0336	0,0286	0,0508
Median	20,917	20,818	20,749	20,655	20,585

Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
0,223	0,276	0,356	0,448	0,527

	BUK-VODA [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	21,532	21,480	21,321	21,210	21,015
2.	21,553	21,506	21,319	21,186	21,038
3.	21,553	21,487	21,332	21,165	21,037
4.	21,547	21,480	21,317	21,164	21,015
5.	21,528	21,486	21,295	21,153	21,015
Průměr	21,543	21,488	21,317	21,176	21,024
Smdch	0,0118	0,0107	0,0135	0,0226	0,0123
Median	21,547	21,486	21,319	21,165	21,015

	Hloubka odstraněné vrstvy [mm]			
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
-0,007	0,047	0,218	0,360	0,511

	BUK-VODA [mm]				
Č.M.	30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
1.	21,453	21,284	21,045	20,961	20,777
2.	21,462	21,258	21,102	20,973	20,816
3.	21,480	21,329	21,073	20,944	20,813
4.	21,426	21,363	21,131	21,018	20,829
5.	21,416	21,341	21,127	21,045	20,766
6.	21,454	21,289	21,084	20,916	20,787
7.	21,506	21,284	21,060	20,913	20,727
8.	21,452	21,279	21,089	20,972	20,789
9.	21,426	21,271	21,032	20,985	20,812
10.	21,392	21,377	21,110	20,979	20,759
Průměr	21,447	21,308	21,085	20,971	20,788
Smdch	0,0330	0,0415	0,0333	0,0411	0,0313
Median	21,453	21,287	21,087	20,973	20,788

Hloubka odstraněné vrstvy [mm]				
30/100 [W]	40/100 [W]	50/100 [W]	60/100 [W]	70/100 [W]
0,011	0,151	0,373	0,488	0,671